

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

0 377 073  
A2

USSD 7269

(12)

# EUROPEAN PATENT APPLICATION

(21) Application number: 89110307.9

(51) Int. Cl.<sup>5</sup>: H01L 39/24, C04B 35/50

(22) Date of filing: 07.06.89

(30) Priority: 07.12.88 JP 309661/88  
07.12.88 JP 309662/88

(43) Date of publication of application:  
11.07.90 Bulletin 90/28

(84) Designated Contracting States:  
DE FR GB

(71) Applicant: Mitsubishi Metal Corporation  
No. 5-2, Ohtemachi, 1-chome Chiyoda-ku  
Tokyo 100(JP)

(72) Inventor: Sugihara, Tadashi c/o Mitsubishi  
Metal Corp.  
Chuo Kenkyujo, 297, Kitabukurocho 1-chome  
Omiya-shi Saitama 330(JP)  
Inventor: Ohuchi, Yukihiro c/o Mitsubishi  
Metal Corp.  
Chuo Kenkyujo, 297, Kitabukurocho 1-chome  
Omiya-shi Saitama 330(JP)  
Inventor: Takeshita, Takuo c/o Mitsubishi  
Metal Corp.  
Chuo Kenyujo, 297, Kitabukurocho 1-chome  
Omiya-shi Saitama 330(JP)

(74) Representative: Pätzold, Herbert, Dr.-Ing.  
Steubstrasse 10  
D-8032 Gräfelfing/München(DE)

(54) Sputtering target used for forming quinary superconductive oxide.

(57) A target used for forming a thin film of a quinary superconductive oxide contains metal copper ranging between about 8 % and about 40 % by volume dispersed into a quaternary or a quinary complex oxide, and the metal copper improves the thermal conductivity and the electrical conductivity of the target, so that cracks are less liable to take place in the target and the target is applicable to a d.c. sputtering system, thereby decreasing the production cost of the thin film.

EP 0 377 073 A2

## SPUTTERING TARGET USED FOR FORMING QUINARY SUPERCONDUCTIVE OXIDE

FIELD OF THE INVENTION

5 This invention relates to a target used in a sputtering system and, more particularly, to a target used for a superconductive film of a quinary superconductive oxide.

BACKGROUND OF THE INVENTION

10

Many attempts are made for depositing a quinary superconductive oxide in such as, for example, the thallium-barium-calcium-copper-oxide (Tl-Ba-Ca-Cu-O) system or the bismuth-strontium-calcium-copper-oxide (Bi-Sr-Ca-Cu-O) system on an insulating substrate. The sputtering technique is an attractive candidate for the formation of the quinary superconductive oxide, and, for this reason, various targets are proposed for use in the sputtering system.

15

One of the formation processes starts with preparation of raw powders of thallium oxide, barium carbonate, calcium carbonate and copper oxide, and these powders are about 10 microns in average diameter. The raw powders are regulated to a predetermined proportion, and then, mixed to produce a mixture. The mixture is calcined in a sealed vessel at 600 degrees to 700 degrees in centigrade for a certain time period, and the calcined product is pulverized into a powder. The calcining stage and the pulverizing stage are repeated twice or three times, thereby forming a powder of a superconductive oxide in the thallium-strontium-calcium-copper-oxide system. The powder of the superconductive oxide is formed into a target by using a hot -pressing technique. Namely, the powder is pressurized at 100 kgf/cm<sup>2</sup> to 200 kgf/cm<sup>2</sup> and subjected to a heat treatment in a vacuum ambient less than 10<sup>-2</sup> torr at 800 degrees to 900 degrees in centigrade for a time period ranging from an hour to four hours. The target thus formed substantially consists of a quinary oxide in the thallium-barium-calcium-copper-oxide system or a composite of the quinary oxide and copper oxide equal to or less than 20 % in volume. The reason why the copper oxide is intentionally included in the target is that the composition of the target is hardly transferred to the deposited film under certain sputtering conditions and, for this reason, the copper oxide is previously supplemented to the powder of the superconductive oxide.

30

The formation of the target of the quinary superconductive oxide in bismuth-strontium-calcium-copper system traces the similar process sequence to that described above. Namely, a mixture is prepared from raw powders of bismuth oxide, strontium carbonate, calcium carbonate and copper oxide which are about 10 microns in average diameter. A powder of lead oxide may be further mixed into the mixture. The mixture is calcined at 700 degrees and 800 degrees in centigrade for a certain time period, and the calcined product is pulverized into a powder. These are repeated twice or three times, thereby finally producing a powder of superconductive oxide in the bismuth-strontium-calcium-copper-oxide system. With the superconductive oxide powder, a target is formed by using a hot-pressing technique in the aforementioned conditions. The target thus produced is substantially composed of a superconductive oxide in either bismuth-strontium-calcium-copper or bismuth-strontium-calcium-copper-oxide system. If the excess copper oxide is previously into the mixture so as to adjust the composition of the deposited oxide film, the target contains the copper oxide equal to or less than 20 % by volume.

40

However, a problem is encountered in the prior art target in production of cracks due to thermal stress. This is because of the fact that the prior art target is small in thermal conductivity, and, for this reason, a large difference in temperature takes place between both sides of the target in the service conditions. The large difference in temperature results in thermal stress which is causative of the cracks. The cracks deteriorates the production yield and, accordingly, increases the production cost of the deposited film.

45

The prior art target is further small in electric conductivity, so that the prior art target is merely applicable to an expensive r.f. sputtering system. This also increases the production cost of the deposited film.

50

Another problem inherent in the prior art target is brittleness. The operator is requested to carefully handle the brittle target, however, the operator sometimes makes human errors. This results in destruction of the target, and, for this reason, the production cost of the deposited film further tends to be increased.

SUMMARY OF THE INVENTION

It is therefore an important object of the present invention to provide a target large in thermal conductivity as well as electrical conductivity.

It is also an important object of the present invention to provide a target which is large in mechanical strength and, accordingly, less liable to be destroyed.

To accomplish these objects, the present invention proposes to disperse metal copper into a quaternary and/or quinary oxide used for formation of a superconductive film. The metal copper is conducive to improvement in thermal conductivity, electric conductivity as well as in mechanical strength.

In accordance with one aspect of the present invention, there is provided a target used in a sputtering system for forming a thin film of a quinary superconductive oxide, comprising a quaternary complex oxide containing elements selected from the elements of said quinary superconductive oxide and metal copper ranging between about 8 % and about 40 % by volume, wherein the metal copper is dispersed into the quaternary complex oxide.

In accordance with another aspect of the present invention, there is provided a target used in a sputtering system for forming a thin film of a quinary superconductive oxide, comprising a quinary complex oxide containing all of the elements of said quinary superconductive oxide and metal copper ranging between about 8 % and about 40 % by volume, wherein said metal copper is dispersed into said quinary complex oxide.

The copper content is fallen within the range from about 8 % to about 40 % by volume. This is because of the fact that any copper content less than 8 % can not achieve an effective cooling efficiency for restriction of the difference in temperature between both sides, a low electric resistivity acceptable to a current d.c. sputtering system, and a flexural strength preventing the target from destruction. If the copper content is increased over 40 % by volume, the copper is too much to form a complex oxide with the composition desirable for achievement of the superconductivity. The problem in the excess copper content is especially eminent in the presence of the copper oxide contained in the target.

The target may contain both quaternary and quinary complex oxides and is allowed to contain a copper oxide equal to or less than 20 % by volume.

The quaternary complex oxide may be in either thallium-barium-calcium-oxide or bismuth-strontium-calcium-oxide system, and the quinary complex oxide may be in either thallium-barium-calcium-copper-oxide or bismuth-strontium-calcium-copper-system.

DESCRIPTION OF THE PREFERRED EMBODIMENTSThallium-Barium-Calcium-Copper-Oxide System

In order to produce a target according to the present invention, it is necessary to prepare various mixtures in the thallium-barium-calcium-oxide system and the thallium-barium-calcium-copper-oxide system the compositions of which are indicated in Table 1. Each of the mixtures is equal to or less than five microns in average diameter, and referred to as specimen designated by one of the numerals 1 to 11.

Each of the mixtures are shaped into a disk configuration by using a vacuum hot-pressing technique, and the disk-shaped target is about 50 millimeters in diameter and about 4 millimeters in thickness. The hot pressing is carried out in a vacuum ambient of about  $10^{-3}$  torr at about 750 degrees in centigrade for about three hours, and the mixture is pressurized at about 150 kgf/cm<sup>2</sup>.

Other ingredient mixtures (which respectively consist of specimens 12 to 17) are prepared for the sake of comparison. The mixtures or the specimens 12 to 15 are out of the scope of the present invention due to the copper contents, and these mixtures are also shaped into the disk configuration by using the vacuum hot pressing technique. The conditions of the hot pressing are similar to those for the specimens 1 to 11. The specimens 16 and 17 are also out of the scope of the present invention, because no metal copper is contained therein. These mixtures without any metal copper are hot pressed in the similar ambient with the exception that the vacuum ambient is heated to about 850 degrees in centigrade.

The thermal conductivity, the resistivity and the flexural strength are measured for evaluation of all of the targets formed of the specimens 1 to 17. The results are indicated in Table 2.

All of the targets are successively installed in a d.c. sputtering system, and, then, subjected to

bombardments of argon ions, respectively. Additionally, an r.f. magnetron sputtering system is alternatively usable for the deposition of the thin films. Thus, thin films are deposited to a thickness of about 2 microns on respective substrates. The sputtering conditions are as follows:

Vacuum;	$10^{-4}$ torr to $10^{-1}$ torr,
Gas;	argon, (gaseous mixture of argon and oxygen (5 % to 50 %) are available)
Power;	100 watts to 600 watts,
Substrate;	magnesium oxide (MgO) substrates having rectangular top surface measuring about 100 millimeters x 100 millimeters.
Heat application to the substrates;	
	about 650 degrees in centigrade, (no heat application is acceptable)
Distance between the target and the substrate;	
	about 50 millimeters to about 130 millimeters.

After the deposition of the thin films, the substrates are placed in a thallium (Tl) ambient of about 840 degrees in centigrade for about 50 hours to carry out a heat treatment. After the heat treatment, the substrates are gradually cooled, and, thereafter, critical temperatures  $T_c$  ( or temperatures of zero resistivity) are respectively measured for all of the thin films by using the four probe method.

The measured critical temperatures  $T_c$  are also indicated in Table 2. In Table 2, the target respectively produced by the specimens 1 to 17 and the thin films deposited by using the respective targets are labeled by the same numerals used for indication of the specimens.

(blank)

Table 1

specimen	Mixture (% by volume)							
	Ti-Ba-Ca-(Cu)-O system						CuO	Cu
	percentage by weight							
	Ti	Ba	Ca	Cu	O			
1	46.0	30.9	10.4	-	residual	residual	-	17.2
2	46.0	30.9	10.4	-	residual	residual	-	34.2
3	29.1	39.0	17.1	-	residual	residual	17.1	9.6
4	29.1	39.0	17.1	-	residual	residual	4.3	18.0
5	36.7	24.6	7.2	17.1	residual	residual	-	8.5
6	36.7	24.6	7.2	17.1	residual	residual	-	12.3
7	39.5	26.5	7.8	12.3	residual	residual	3.2	10.8
8	39.5	26.5	7.8	12.3	residual	residual	11.8	15.7
9	46.0	30.9	10.4	-	residual	28.1	-	37.4
	29.1	39.0	17.1	-	residual	residual		
10	29.1	39.0	17.1	-	residual	39.1	6.8	15.1
	36.7	24.6	7.2	17.1	residual	residual		
11	36.7	24.6	7.2	17.1	residual	43.0	12.5	9.2
	39.5	26.5	7.8	12.3	residual	residual		
12	46.0	30.9	10.4	-	residual	residual	-	43.2
13	29.1	39.0	17.1	-	residual	residual	17.1	6.5
14	36.7	24.6	7.2	17.1	residual	residual	-	6.1
15	39.5	26.5	7.8	12.3	residual	residual	3.2	44.1
16	36.7	24.6	7.2	17.1	residual	residual	-	-
17	36.7	24.6	7.2	17.1	residual	residual	6.8	-

Table 2

Speci- men	T.C. ( <u>Cal</u> ) cm·sec·degree	Resistivity (ohm·cm)	Flexural strength (Kg/cm <sup>2</sup> )	Critical Temp. (Kelvin)
1	0.25	$8 \times 10^{-6}$	130	120
2	0.30	$3 \times 10^{-6}$	150	80
3	0.10	$15 \times 10^{-6}$	146	115
4	0.25	$7 \times 10^{-6}$	135	113
5	0.08	$20 \times 10^{-6}$	121	118
6	0.11	$14 \times 10^{-6}$	143	116
7	0.11	$15 \times 10^{-6}$	137	121
8	0.20	$10 \times 10^{-6}$	156	87
9	0.35	$2 \times 10^{-6}$	145	103
10	0.18	$8 \times 10^{-6}$	137	94
11	0.10	$18 \times 10^{-6}$	131	89
12	0.45	$2 \times 10^{-6}$	142	60
13	0.01	$6 \times 10^{-3}$	67	108
14	0.01	$5 \times 10^{-3}$	70	105
15	0.45	$2 \times 10^{-6}$	140	58
16	0.01	3	70	88
17	0.01	5	70	114

T.C. stands for "thermal conductivity", and "degree" is in centigrade.

As will be understood from Table 2, the targets produced of the mixtures according to the present invention are improved in the thermal conductivity, the resistivity and the flexural strength in comparison with the targets produced of the mixtures out of the scope of the present invention. The targets of the present invention are thus increased in the thermal conductivity, so that the targets are effectively cooled off so as to prevent the targets from production of the cracks. This results in prolonging the service time of each target, which in turn results in reduction of the production cost of the thin film. The resistivity is low enough to use the d.c. sputtering system, and this also is conducive to reduction of the production cost. The large flexural strength enhances the operability of each target, and the target is less liable to break. This further improves the production cost.

Comparing targets produced of the specimens 13 and 14 with the targets of the present invention, it is understood that no improvement is achieved in the thermal conductivity, the resistivity and the flexural strength. The targets produced of the specimens 12 and 15 suffer from the low critical temperatures.

respectively. It is considered that the excess copper restricts the formation of the superconductive film.

#### Bismuth-Strontium-Calcium-Copper System

The process sequence for formation of the targets according to the present invention starts with preparation of various mixtures in the bismuth-strontium-calcium-oxide system and the bismuth-strontium-calcium-copper system the compositions of which are indicated in Table 3. Each of the mixtures is equal to or less than five microns in average diameter, and referred to as specimen designated by one of the numerals 1 to 11.

Each of the mixtures are shaped into a disk configuration by using a vacuum hot-pressing technique, and the disk-shaped target is about 50 millimeters in diameter and about 4 millimeters in thickness. The hot pressing is carried out in a vacuum ambient of about  $10^{-3}$  torr at about 750 degrees in centigrade for about three hours, and the mixture is pressurized at about 150 kgf/cm<sup>2</sup>.

Other ingredient mixtures (which respectively consist of specimens 12 to 17) are prepared for the sake of comparison. The mixtures or the specimens 12 to 15 are out of the scope of the present invention due to the copper contents, and these mixtures are also shaped into the disk configuration by using the vacuum hot pressing technique. The conditions of the hot pressing are similar to those for the specimens 1 to 11. The specimens 16 and 17 are also out of the scope of the present invention, because no metal copper is contained therein. These mixtures without any metal copper are hot pressed in the similar ambient with the exception that the vacuum ambient is heated to about 850 degrees in centigrade.

The thermal conductivity, the resistivity and the flexural strength are measured for evaluation of all of the targets formed of the specimens 1 to 17. The results are indicated in Table 4.

All of the targets are successively installed in a d.c. sputtering system, and, then, subjected to bombardments of argon ions, respectively. Additionally, an r.f. magnetron sputtering system is alternatively usable for the deposition of the thin films. Thus, thin films are deposited to a thickness of about 2 microns on respective substrates. The sputtering conditions are as follows:

Vacuum;	$10^{-4}$ torr to $10^{-1}$ torr,
Gas;	argon, (gaseous mixture of argon and oxygen (5 % to 50 % ) are available)
Power;	100 watts to 600 watts,
Substrate;	magnesium oxide (MgO) substrates having rectangular top surface measuring about 10 millimeters x 10 millimeters,
Heat application to the substrates;	
	about 700 degrees in centigrade, (no heat application is acceptable)
Distance between the target and the substrate;	
	about 50 millimeters to about 130 millimeters.

After the deposition of the thin films, the substrates are placed in the atmospheric ambient at 850 degrees in centigrade for about 30 hours to carry out a heat treatment. After the heat treatment, the substrates are gradually cooled, and, thereafter, critical temperatures  $T_c$  ( or temperatures of zero resistivity) are respectively measured for all of the thin films by using the four probe method.

The measured critical temperatures  $T_c$  are also indicated in Table 4. In Table 2, the target respectively produced by the specimens 1 to 17 and the thin films deposited by using the respective targets are labeled by the same numerals used for indication of the specimens.  
(blank)

Table 3

specimen	composition (by volume)								
	Bi-Sr-Ca-(Cu)-O system							CuO	Cu
	percentage by weight								
	Bi	Pb	Sr	Ca	Cu	O			
1	53.2	-	22.3	10.2	-	residual	residual	-	17.8
2	53.2	-	22.3	10.2	-	residual	residual	-	30.3
3	58.4	-	16.3	11.2	-	residual	residual	18.8	8.5
4	58.4	-	16.3	11.2	-	residual	residual	7.3	17.8
5	38.7	9.6	20.3	9.3	7.4	residual	residual	-	9.5
6	38.7	9.6	20.3	9.3	7.4	residual	residual	-	17.4
7	47.1	-	19.7	4.5	14.3	residual	residual	4.9	12.2
8	47.1	-	19.7	4.5	14.3	residual	residual	10.9	27.2
9	53.2	-	22.3	10.2	-	residual	28.1	-	35.0
	58.4	-	16.3	11.2	-	residual	residual		
10	53.2	-	22.3	10.2	-	residual	39.1	2.0	14.1
	38.7	9.6	20.3	9.3	7.4	residual	residual		
11	38.7	9.6	20.3	9.3	7.4	residual	43.0	13.7	9.0
	47.1	-	19.7	4.5	14.3	residual	residual		
12	53.2	-	22.3	10.2	-	residual	residual	-	6.1
13	58.4	-	16.3	11.2	-	residual	residual	18.8	45.3
14	38.7	9.6	20.3	9.3	7.4	residual	residual	-	6.0
15	47.1	-	19.7	4.5	14.3	residual	residual	4.9	42.1
16	47.1	-	19.7	4.5	14.3	residual	residual	-	-
17	40.8	-	17.1	7.8	18.6	residual	residual	7.5	-



Table 4

specimen	T.C Cal (cm.sec.degree)	Resistivity (ohm. cm)	Flexural strength (Kg/cm <sup>2</sup> )	Critical Temp. (Kelvin)
1	0.20	10x10 <sup>-6</sup>	143	103
2	0.35	3x10 <sup>-6</sup>	127	73
3	0.10	25x10 <sup>-6</sup>	136	85
4	0.20	10x10 <sup>-6</sup>	150	88
5	0.10	20x10 <sup>-6</sup>	128	104
6	0.21	9x10 <sup>-6</sup>	133	103
7	0.13	17x10 <sup>-6</sup>	147	82
8	0.27	5x10 <sup>-6</sup>	125	75
9	0.40	2x10 <sup>-6</sup>	130	97
10	0.16	14x10 <sup>-6</sup>	135	95
11	0.09	22x10 <sup>-6</sup>	125	90
12	0.01	5x10 <sup>-3</sup>	63	100
13	0.45	2x10 <sup>-6</sup>	140	57
14	0.01	4x10 <sup>-3</sup>	70	97
15	0.45	2x10 <sup>-6</sup>	136	53
16	0.01	7	85	76
17	0.01	1	67	101

As will be understood from Table 4, the targets produced of the mixtures according to the present invention are improved in the thermal conductivity, the resistivity and the flexural strength in comparison with the targets produced of the mixtures out of the scope of the present invention. The targets of the present invention are thus increased in the thermal conductivity, so that the targets are effectively cooled off so as to prevent the targets from production of the cracks. This results in prolonging the service time of each target, which in turn results in reduction of the production cost of the thin film. The resistivity is low enough to use the d.c. sputtering system, and this also is conducive to reduction of the production cost. The large flexural strength enhances the operability of each target, and the target is less liable to break. This further improves the production cost.

Comparing targets produced of the specimens 13 and 14 with the targets of the present invention, it is understood that no improvement is achieved in the thermal conductivity, the resistivity and the flexural strength. The targets produced of the specimens 12 and 15 suffer from the low critical temperatures, respectively. It is considered that the excess copper restricts the formation of the superconductive film.

Although particular embodiments of the present invention have been shown and described, it will be obvious to those skilled in the art that various changes and modifications may be made without departing

from the spirit and scope of the present invention.

### Claims

5

1. A target used in a sputtering system for forming a thin film of a quinary superconductive oxide, comprising at least a quaternary complex oxide containing elements selected from the elements of said quinary superconductive oxide, characterized by metal copper ranging between about 8 % and about 40 % by volume, and in that said metal copper is dispersed into said quaternary complex oxide.

10

2. A target used in a sputtering system for forming a thin film of a quinary superconductive oxide as set forth in claim 1, in which said target further comprises a quinary complex oxide containing all of the elements of said quinary superconductive oxide.

15

3. A target used in a sputtering system for forming a thin film of a quinary superconductive oxide as set forth in claim 1, in which said target further comprises a copper oxide equal to or less than about 20 % by volume.

20

25

30

35

40

45

50

55

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

0 377 073  
A3

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number: 89110307.9

(51) Int. Cl.<sup>5</sup>: H01L 39/24, C04B 35/50,  
C23C 14/34

(22) Date of filing: 07.06.89

(30) Priority: 07.12.88 JP 309661/88  
07.12.88 JP 309662/88

(43) Date of publication of application:  
11.07.90 Bulletin 90/28

(84) Designated Contracting States:  
DE FR GB

(88) Date of deferred publication of the search report:  
07.11.90 Bulletin 90/45

(71) Applicant: Mitsubishi Metal Corporation  
No. 5-2, Ohtemachi, 1-chome Chiyoda-ku  
Tokyo 100(JP)

(72) Inventor: Sugihara, Tadashi c/o Mitsubishi  
Metal Corp.  
Chuo Kenkyujo, 297, Kitabukurocho 1-chome  
Omiya-shi Saitama 330(JP)  
Inventor: Ohuchi, Yukihiro c/o Mitsubishi  
Metal Corp.  
Chuo Kenkyujo, 297, Kitabukurocho 1-chome  
Omiya-shi Saitama 330(JP)  
Inventor: Takeshita, Takuo c/o Mitsubishi  
Metal Corp.  
Chuo Kenkyujo, 297, Kitabukurocho 1-chome  
Omiya-shi Saitama 330(JP)

(74) Representative: Pätzold, Herbert, Dr.-Ing.  
Steubstrasse 10  
D-8032 Gräfelfing/München(DE)

(54) Sputtering target used for forming quinary superconductive oxide.

(57) A target used for forming a thin film of a quinary superconductive oxide contains metal copper ranging between about 8 % and about 40 % by volume dispersed into a quaternary or a quinary complex oxide, and the metal copper improves the thermal conductivity and the electrical conductivity of the target, so that cracks are less liable to take place in the target and the target is applicable to a d.c. sputtering system, thereby decreasing the production cost of the thin film.

EP 0 377 073 A3



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number

EP 89 11 0307

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	JAPANESE JOURNAL OF APPLIED PHYSICS. letters vol. 26, no. 9, September 1987, TOKYO JP pages 1484 - 1486; H. OHKUMA et al: "Preparation of Y-Ba-Cu-O thin films by rf-magnetron sputtering" * page 1484 *	1-4	H01L39/24 C04B35/50 C23C14/34
A	APPLIED PHYSICS LETTERS. vol. 52, no. 20, 16 May 1988, NEW YORK US pages 1732 - 1734; H. AKOH et al: "Thickness dependence of superconductivity in rf-sputtered Y-Ba-Cu-O thin films" * page 1732 *	1-4	
A	JAPANESE JOURNAL OF APPLIED PHYSICS. letters vol. 27, no. 3, March 1988, TOKYO JP pages 378 - 380; M. NAKAO et al: "Magnetron sputtering of Bi-Ca-Sr-Cu-O thin films with superconductivity above 80K" * page 378 *	1	
E	WO-A-8905283 (MITSUBISHI) * abstract *	1-4	TECHNICAL FIELDS SEARCHED (Int. Cl.5)  H01L C23C
The present search report has been drawn up for all claims			
Place of search BERLIN		Date of completion of the search 27 AUGUST 1990	Examiner ROUSSEL A. T.
<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document  T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons  & : member of the same patent family, corresponding document			